

PRODUCT RANGE

IPNZ Item	IPNZ Description
EBM0006	500MM x 2200M x 17UM IPEX MACHINE FILM

Properties				
Measurement	Unit	Target	Test Method	
Colour		Clear Natural		
Film Width	mm	500 (+/- 3mm)	Measuring Tape	
Roll Length	М	2200		
Gauge	um	17 (+/- 2um)	Thickness Gauge	
Roll Weight	kg	17.2KG (+/- 3%)	Electronic Scale	
Tensile Properties Ultimate Stress	MPa	MD 39.3 TD 30.4	ASTM D882	
Tensile Properties Elongation	%	MD 649 TD 806	ASTM D882	
Puncture Impact Strength (F50)	g	106	ASTM D1709	
Elmendorf Tear Resistance	mN	MD 1240 TD 5070	ASTM D1922	
Core size ID	mm	77		
Pallet		IP Printed 1200 x 1200mm		
Rolls per pallet		50		
Storage		Before film is used it should be kept out of direct natural light/sunlight and in a well-ventilated area at a cool ambient temperature.		
Product Stewardship and Recyclability		Industrial plastics waste companies and recyclers can collect this material for recycling where enough clean PE film is available.		
		This stretch film is code 4 for New Zealand recycling purposes.		
		Cardboard cores can be recycled by Industrial recyclers if film and tape is removed. Cardboard layer pads and wrapping used as packaging on the pallet can be recycled using typical recycling channels.		
Food Contact		This film is intended for use as secondary and tertiary packaging material not in direct food contact.		

This technical data sheet and the information contained therein are the property of Integrated Packaging and are disclosed to the specified Customer in confidence. This document must not be copied or otherwise disclosed to any other person or corporation without written permission from Integrated Packaging. The Information tabled are nominal values and do not constitute as a specification.