



NORDIC DRY (UK) LTD

12 Winchfield Way Rickmansworth England WD3
4DN UNITED KINGDOM

Mobile: +44 (0) 7818 117073
E-mail: gavin.kramer@nordicdry.com
Web:www.nordicdry.com

Product specification

1.Name

Code	NP1000GR
Name	Nordic Green Piccolo 1000GR

2.Formula

CaCl ₂ powder	Coco peat
Anhydrous CaCl ₂	MC of peat < 15%

3.Size of inner packing bag

Inner bag size	Horizontal width	240±5 mm	Edge sealing width	10±2 mm
	Longitudinal length	290±10 mm		10±2 mm
Inner bag weight	1000G (950~1050G)			
Inner bag material spec.	500mm non-woven fabric with film			

4.Size of outer packing bag

Outer bag size	Horizontal width	250±5 mm	Edge sealing width	10±2 mm
	Longitudinal length	350±10 mm		10±2 mm
Outer bag material spec.	700mm spunlace nonwoven fabric with film			

5.Finished size

Finished size	Horizontal width	390±10 mm	Edge sealing width	10±2 mm
	Longitudinal length	300±10 mm		10±2 mm
Bags form	Bag(Stitching edge)+Blue hanger			

6.Packing way

Carton	NordicDry customized carton 370×275×330mm		
Inside packing,10units/carton. Two kinds of vacuum plastic bags are available, packing according to specific order requirements.	20units/PE bag		
	1 unit/PE bag.		
Carton label	Refer to below mode		




NORDIC DRY (UK) LTD
12 Winchfield Way Rickmansworth England WD3
4DN UNITED KINGDOM

Mobile: +44 (0) 7818 117073
E-mail: gavin.kramer@nordicdry.com
Web: www.nordicdry.com

7.Layout drawing



Warning text mode



Carton label mode

Product Name: Calcium chloride desiccant
Composition: CaCl₂ 80% + Plant Fiber 20%

Batch No.:
NORDIC DRY
PICCOLO 1000
Contents 20Pcs
Gross Weight 21Kg
Net Weight 20Kg

Made in China



NORDIC DRY (UK) LTD

12 Winchfield Way Rickmansworth England WD3
4DN UNITED KINGDOM

Mobile: +44 (0) 7818 117073
E-mail: gavin.kramer@nordicdry.com
Web: www.nordicdry.com

8.Finished product picture



9.Test report.

(NO.)	(Sample name)	Remarks
①	Non-woven packing 1kg calcium chloride desiccant	Nordic China
②	Non-woven packing 1kg calcium chloride desiccant	Nordic China
③	Non-woven packing 1kg calcium chloride desiccant	Nordic China


Date of receipt of sample: 2018.12.15 Sample test date: 2018.12.15~2029.01.04

Test requirements:

At 60℃, RH=90%, the moisture absorption capacity of the test sample, need to record data once a day

Test results:

Date/Time	Time s(d)	weight (g)		
		Moisture absorption rate%		
		Nordic China		
		①	②	③
15/12/18 4:00 p.m.	0d	1025	1060	995
16/12/18 4:00 p.m.	1d	1445	1570	1475
		41.0%	48.1%	48.2%
17/12/18 4:00 p.m.	2d	1710	1850	1730
		66.8%	74.5%	73.9%
18/12/18 4:00 p.m.	3d	1930	2070	1915
		88.3%	95.3%	92.5%
19/12/18 4:00 p.m.	4d	2115	2245	2085
		106.3%	111.8%	109.6%
20/12/18 4:00 p.m.	5d	2285	2410	2245
		122.9%	127.4%	125.6%
21/12/18 4:00 p.m.	6d	2400	2520	2340
		134.1%	137.7%	135.2%
22/12/18 4:00 p.m.	7d	2530	2665	2465
		146.8%	151.4%	147.7%
24/12/18 4:00 p.m.	9d	2720	2840	2640
		165.4%	167.9%	164.3%
25/12/18 4:00 p.m.	10d	2790	2900	2700
		172.2%	17360.0%	171.4%
26/12/18 4:00 p.m.	11d	2865	2970	2770
		179.5%	180.2%	178.4%
27/12/18 4:00 p.m.	12d	2930	3035	2835
		185.9%	186.3%	184.9%
28/12/18 4:00 p.m.	13d	2985	3095	2885
		191.2%	192.0%	189.9%
29/12/18 4:00 p.m.	14d	3035	3135	2940
		196.1%	195.8%	195.5%
02/01/18 4:00 p.m.	18d	3275	3335	3200
		219.5%	214.6%	221.6%
03/01/18 4:00 p.m.	19d	—	3305	3310
		—	211.8%	232.7%
04/01/18 4:00 p.m.	20d	—	3265	3325
		—	208.0%	234.2%



Note:

1. On the 20 days of testing, no leakage was observed.
2. During the test, the sample A dropped inadvertently and water seepage occurred, so the test was terminated.

Lab director:

Inspector: 赵玉玲

Nordic China R&D Center Lab.

2018-01-04

This report is considered invalidated without the Special Seal for Inspection of the Nordic. This report shall not be altered, increased or deleted. The results shown in this test report refer only to the sample(s) tested. Without written approval of Nordic, this test report can not be copied except in full and published as advertisement.