

LEIGHTONS

PACKAGING SOLUTIONS

Grease Guard Lite

Physical Test		Test Method	Basic-Weight*(g/m ²)	
Kind of Test		Reference	30	32
Basis Weight		T410 om-98	30 ± 2	32 ± 2
Thickness		ISO 534:2011	35 – 41	38 – 44
Smoothness (Bekk)	FS	T479 om-91	≥ 50	≥ 50
	WS		≥ 20	≥ 20
Porosity		ISO 5636/3/92	≤ 100	
Tensile	MD	T494 om-96	≥ 3.4	≥ 3.6
	CD		≥ 1.9	≥ 2.0
Wet Strength Ratio		MD	≥ 10	
Tearing	MD	T414 om-98	≥ 10	≥ 11
	CD		≥ 12	≥ 13
Bursting		T403 om-97	≥ 90	≥ 100

Food Contact Approval



TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGES.

CONCLUSION:

TESTED SAMPLE
SUBMITTED SAMPLE

STANDARD
TEST FOR F.D.A. REGULATION ON PAPER/PAPERBOARD
— AS PER U.S. FOOD AND DRUGS ADMINISTRATION 21 CFR PART 176.170

RESULT
PASS

Chain of Custody Approval

The COC requirements of the PEFC Council Technical Document as set by the PEFC Council (Programme for the Endorsement of Forest Certification schemes), and Control Union Certifications (CU) Inspection Regulations.

PEFC ST 2002:2020, PEFC ST 2001:2020

Valid until: 17 January 2028

- This product is recyclable, home compostable and biodegradable
- This paper is Elemental Chlorine Free (ECF) with no additional Chlorine bleaching during the papermaking process.

Certification is valid until 14th Feb 2025



V2 5/11/24